

ALCUDIA® EBA PA-1770

乙烯丙烯酸丁酯共聚物

REPSOL

产品说明

EBA ALCUDIA® PA-1770 is a copolymer suitable for general extrusion, injection moulding and compounds where good processability, flexibility and very good mechanical properties are required. The butyl acrylate content is 17%. It contains antioxidant additives.

TYPICAL APPLICATIONS

Extrusion (profiles, sheets)

Injection moulding

Microcellular foams

Compounds and masterbatches

Cables

Recommended melt temperature 180°C. EBA copolymers exhibit excellent thermal stability, which allows higher processing temperatures if needed. Processing characteristics of PA-1770 are similar to LDPE and conventional polyethylene extruders are recommended. Processing conditions should be optimised for each production line.

基本信息

添加剂	抗氧化性			
-----	------	--	--	--

特性	抗氧化性	可加工性,良好	良好的柔韧性	食品接触的合规性
----	------	---------	--------	----------

用途	电线电缆应用	复合	母料	泡沫
----	--------	----	----	----

用途	片材	型材		
----	----	----	--	--

机构评级	欧洲 食品接触, 未评级			
------	--------------	--	--	--

加工方法	复合	挤出	片材挤出成型	型材挤出成型
------	----	----	--------	--------

加工方法	注射成型			
------	------	--	--	--

物理性能	额定值	单位制	测试方法
------	-----	-----	------

密度 (23°C)	0.924	g/cm ³	ISO 1183
-----------	-------	-------------------	----------

熔流率(熔体流动速率) (190°C/2.16 kg)	7.0	g/10 min	ISO 1133
-----------------------------	-----	----------	----------

丁酯丙烯酸成分	17.0	wt%	
---------	------	-----	--

硬度	额定值	单位制	测试方法
----	-----	-----	------

肖氏硬度			ISO 868
------	--	--	---------

邵氏 A	90		ISO 868
------	----	--	---------

邵氏 D	33		ISO 868
------	----	--	---------

机械性能	额定值	单位制	测试方法
------	-----	-----	------

拉伸应力 (断裂)	12.0	MPa	ISO 527-2
-----------	------	-----	-----------

拉伸应变 (断裂)	800	%	ISO 527-2
-----------	-----	---	-----------

热性能	额定值	单位制	测试方法
-----	-----	-----	------

维卡软化温度	61.0	°C	ISO 306/A
--------	------	----	-----------

熔融温度	93.0	°C	
------	------	----	--

注射	额定值	单位制	
----	-----	-----	--

加工(熔体)温度	180	°C	
----------	-----	----	--

挤出	额定值	单位制	
----	-----	-----	--

熔体温度	180	°C	
------	-----	----	--