

# Fusabond® M603

聚乙烯共聚物

## DuPont Packaging & Industrial Polymers

### 产品说明

Fusabond® M603 Resin is a random ethylene copolymer, incorporating a monomer which is classified as being a maleic anhydride equivalent for application uses. The exact composition is considered to be proprietary information.

Applications:

Fusabond® M603 is used in a variety of applications where adhesion improvements are needed for coatings, or compatibilization is need for compounds. In these applications, the Fusabond® resin is typically dry blended with a polyolefin matrix polymer for further processing.

Examples include: Adhesives, Polymer Modification, Wood-Plastic Composites

基本信息				
用途	混合	涂层应用	粘合剂	
形式	粒子			
物理性能	额定值	单位制	测试方法	
比重	0.940	g/cm³	ASTM D792, ISO 1183	
熔流率(熔体流动速率) (190°C/2.16 kg)	25	g/10 min	ASTM D1238, ISO 1133	
热性能	额定值	单位制	测试方法	
熔融温度(DSC)	108	°C	ASTM D3418, ISO 3146	
补充信息	额定值	单位制		
Processing Temperature		°C		